

Schnittdaten

Données de coupe

Parametri di lavoro

Cutting data

Art. 52150

Mat.	ϕ 4.00–7.00	ϕ 7.10–10.00	ϕ 10.10–13.00	ϕ 13.10–16.00	ϕ 16.10–20.00
P1	V _c f	90–120 0.080–0.200	90–120 0.180–0.350	90–120 0.300–0.400	90–120 0.350–0.450
P2	V _c f	80–150 0.050–0.180	80–150 0.160–0.250	80–150 0.220–0.350	80–150 0.330–0.400
P3	V _c f				
M1	V _c f				
M2	V _c f				
K1	V _c f	200–250 0.100–0.250	200–250 0.220–0.350	200–250 0.330–0.450	200–250 0.420–0.550
K2	V _c f	160–200 0.080–0.180	160–200 0.160–0.250	160–200 0.230–0.350	160–200 0.330–0.500
N1	V _c f				
N2	V _c f				
N3	V _c f	250–300 0.050–0.150	250–300 0.130–0.250	250–300 0.230–0.350	250–300 0.330–0.450
N4	V _c f				
N5	V _c f	80–120 0.050–0.120	80–120 0.100–0.220	80–120 0.200–0.320	80–120 0.300–0.400
N6	V _c f				
N7	V _c f				
N8	V _c f				
S1	V _c f				
S2	V _c f				
H1	V _c f	70–100 0.050–0.100	70–100 0.080–0.180	70–100 0.160–0.260	70–100 0.240–0.300
H2	V _c f				
H3	V _c f				
O1	V _c f				
O2	V _c f				
O3	V _c f				

Art. 50950

Mat.	ϕ 3.00–5.00	ϕ 5.10–8.00	ϕ 8.10–12.00	ϕ 12.10–16.00	ϕ 16.10–20.00
P1	V _c f	80–120 0.060–0.150	80–120 0.120–0.250	80–120 0.220–0.350	80–120 0.320–0.450
P2	V _c f	60–80 0.050–0.120	60–80 0.100–0.220	60–80 0.200–0.300	60–80 0.280–0.360
P3	V _c f	50–70 0.040–0.100	50–70 0.090–0.180	50–70 0.160–0.260	50–70 0.240–0.320
M1	V _c f	40–60 0.030–0.080	40–60 0.070–0.150	40–60 0.140–0.180	40–60 0.170–0.250
M2	V _c f	30–50 0.030–0.080	30–50 0.070–0.130	30–50 0.120–0.160	30–50 0.150–0.220
K1	V _c f	100–130 0.100–0.250	100–130 0.230–0.350	100–130 0.320–0.450	100–130 0.400–0.500
K2	V _c f	60–80 0.060–0.200	60–80 0.180–0.280	60–80 0.250–0.350	60–80 0.320–0.450
N1	V _c f				
N2	V _c f	150–200 0.100–0.270	150–200 0.250–0.350	150–200 0.330–0.400	150–200 0.380–0.480
N3	V _c f	130–160 0.100–0.250	130–160 0.220–0.320	130–160 0.300–0.380	130–160 0.360–0.450
N4	V _c f				
N5	V _c f				
N6	V _c f				
N7	V _c f				
N8	V _c f				
S1	V _c f	30–60 0.005–0.040	30–60 0.030–0.070	30–60 0.060–0.110	30–60 0.100–0.150
S2	V _c f				
H1	V _c f	60–90 0.050–0.120	60–90 0.100–0.220	60–90 0.200–0.300	60–90 0.280–0.360
H2	V _c f	40–60 0.030–0.070	40–60 0.060–0.130	40–60 0.110–0.180	40–60 0.160–0.240
H3	V _c f	15–35 0.005–0.030	15–35 0.020–0.050	15–35 0.040–0.070	15–35 0.060–0.100
O1	V _c f				
O2	V _c f				
O3	V _c f				

Genannte Werte sind Richtwerte, die je nach Maschine, Aufspannung, Kühlenschmierstoff usw. noch angepasst werden müssen.

Les valeurs mentionnées sont des valeurs recommandées qui doivent être adaptées selon les conditions de la machine, du serrage, du lubrifiant etc.

Questi valori sono valori raccomandati che devono essere adattati secondo le condizioni della macchina, del serraggio, del lubrificante etc.

These are recommended values that depend on the condition of the machine, fixture, coolant etc., and they may have to be adapted yet.