

Schnittdaten

Données de coupe

Parametri di lavoro

Cutting data

Art. 40004

Mat.	ϕ 2.00–5.00	ϕ 6.00–12.00	a_p	a_e
P1	V_c f_z	60–80 0.020–0.060	60–80 0.030–0.110	$0.5 \times d1$
P2	V_c f_z	50–70 0.015–0.060	50–70 0.030–0.110	$0.5 \times d1$
P3	V_c f_z	40–60 0.010–0.050	40–60 0.020–0.100	$0.4 \times d1$
M1	V_c f_z	40–60 0.010–0.050	40–60 0.020–0.100	$0.4 \times d1$
M2	V_c f_z			
K1	V_c f_z	60–80 0.020–0.060	60–80 0.030–0.110	$0.80 \times d1$
K2	V_c f_z	50–70 0.150–0.050	50–70 0.030–0.100	$0.70 \times d1$
N1	V_c f_z			
N2	V_c f_z			
N3	V_c f_z			
N4	V_c f_z			
N5	V_c f_z			
N6	V_c f_z			
N7	V_c f_z			
N8	V_c f_z			
S1	V_c f_z			
S2	V_c f_z			
H1	V_c f_z			
H2	V_c f_z			
H3	V_c f_z			
O1	V_c f_z			
O2	V_c f_z			
O3	V_c f_z			

Art. 47000 / 47500

Mat.	ϕ 2.00–5.00	ϕ 6.00–12.00	ϕ 13.00–20.00	a_p	a_e
P1	V_c f_z				
P2	V_c f_z				
P3	V_c f_z				
M1	V_c f_z				
M2	V_c f_z				
K1	V_c f_z				
K2	V_c f_z				
N1	V_c f_z	300–600 0.030–0.050	300–600 0.050–0.120	$0.120–0.200$	$0.5 \times d1$
N2	V_c f_z	300–1000 0.030–0.060	300–1000 0.060–0.140	$0.140–0.250$	$0.5 \times d1$
N3	V_c f_z	300–1000 0.030–0.060	300–1000 0.060–0.140	$0.140–0.250$	$0.5 \times d1$
N4	V_c f_z				
N5	V_c f_z				
N6	V_c f_z				
N7	V_c f_z				
N8	V_c f_z				
S1	V_c f_z				
S2	V_c f_z				
H1	V_c f_z				
H2	V_c f_z				
H3	V_c f_z				
O1	V_c f_z	300–600 0.030–0.050	300–600 0.050–0.120	$0.120–0.200$	$0.5 \times d1$
O2	V_c f_z				
O3	V_c f_z				

Genannte Werte sind Richtwerte, die je nach Maschine, Aufspannung, Kühlenschmierstoff usw. noch angepasst werden müssen.

Les valeurs mentionnées sont des valeurs recommandées qui doivent être adaptées selon les conditions de la machine, du serrage, du lubrifiant etc.

Questi valori sono valori raccomandati che devono essere adattati secondo le condizioni della macchina, del serraggio, del lubrificante etc.

These are recommended values that depend on the condition of the machine, fixture, coolant etc., and they may have to be adapted yet.