

# Schnittdaten

## Données de coupe

## Parametri di lavoro

## Cutting data

### Art. 43400

Mat.		$\phi$ 1.00–2.00	$\phi$ 3.00–4.00	$\phi$ 5.00–6.00
P1	$v_c$	80–120	80–120	80–120
P1	$f_z$	0.020–0.030	0.030–0.040	0.040–0.050
P2	$v_c$	80–100	80–100	80–100
P2	$f_z$	0.010–0.020	0.020–0.030	0.030–0.040
P3	$v_c$	50–80	50–80	50–80
P3	$f_z$	0.005–0.015	0.015–0.025	0.025–0.035
M1	$v_c$	60–100	60–100	60–100
M1	$f_z$	0.010–0.015	0.015–0.025	0.025–0.035
M2	$v_c$	40–70	40–70	40–70
M2	$f_z$	0.015–0.025	0.025–0.035	0.035–0.045
K1	$v_c$	100–150	100–150	100–150
K1	$f_z$	0.010–0.020	0.020–0.030	0.030–0.040
K2	$v_c$	60–100	60–100	60–100
K2	$f_z$	0.005–0.015	0.015–0.025	0.025–0.035
N1	$v_c$	150–200	150–200	150–200
N1	$f_z$	0.020–0.030	0.030–0.040	0.040–0.050
N2	$v_c$	150–200	150–200	150–200
N2	$f_z$	0.020–0.030	0.030–0.050	0.050–0.060
N3	$v_c$	130–200	130–200	130–200
N3	$f_z$	0.020–0.030	0.030–0.050	0.050–0.060
N4	$v_c$	60–150	60–150	60–150
N4	$f_z$	0.015–0.025	0.025–0.035	0.035–0.045
N5	$v_c$	100–200	100–200	100–200
N5	$f_z$	0.015–0.025	0.025–0.035	0.035–0.045
N6	$v_c$	80–150	80–150	80–150
N6	$f_z$	0.010–0.020	0.020–0.030	0.030–0.040
N7	$v_c$	80–150	80–150	80–150
N7	$f_z$	0.010–0.020	0.020–0.030	0.030–0.040
N8	$v_c$	80–150	80–150	80–150
N8	$f_z$	0.010–0.020	0.020–0.030	0.030–0.040
S1	$v_c$	40–70	40–70	40–70
S1	$f_z$	0.010–0.025	0.020–0.035	0.030–0.045
S2	$v_c$	20–40	20–40	20–40
S2	$f_z$	0.005–0.015	0.015–0.025	0.020–0.035
H1	$v_c$	20–45	25–40	25–40
H1	$f_z$	0.005–0.015	0.015–0.025	0.025–0.035
H2	$v_c$	20–30	15–25	15–25
H2	$f_z$	0.005–0.010	0.010–0.015	0.015–0.020
H3	$v_c$			
O1	$v_c$	100–150	70–110	70–110
O1	$f_z$	0.010–0.020	0.020–0.030	0.030–0.040
O2	$v_c$			
O3	$v_c$			

### Art. 71330

Mat.		$\phi$ 0.20–1.00	$\phi$ 1.00–2.00	$\phi$ 2.00–3.00	$a_p$	$a_e$
P1	$v_c$	40–60	40–60	40–60		
P1	$f_z$	0.002–0.013	0.013–0.020	0.020–0.030	1×d	0.2×d
P2	$v_c$	30–50	30–50	30–50		
P2	$f_z$	0.002–0.012	0.012–0.018	0.018–0.025	1×d	0.2×d
P3	$v_c$					
P3	$f_z$					
M1	$v_c$	25–40	25–40	24–40		
M1	$f_z$	0.002–0.011	0.011–0.016	0.016–0.022	1×d	0.1×d
M2	$v_c$	20–35	20–35	20–35		
M2	$f_z$	0.002–0.010	0.010–0.015	0.015–0.020	1×d	0.1×d
K1	$v_c$	40–60	40–60	40–60		
K1	$f_z$	0.002–0.013	0.013–0.020	0.020–0.030	1×d	0.2×d
K2	$v_c$	35–55	35–55	35–55		
K2	$f_z$	0.002–0.012	0.012–0.018	0.018–0.025	1×d	0.2×d
N1	$v_c$					
N1	$f_z$					
N2	$v_c$	150–200	150–200	150–200		
N2	$f_z$	0.003–0.015	0.015–0.030	0.030–0.050	1×d	0.2×d
N3	$v_c$	150–200	150–200	150–200		
N3	$f_z$	0.002–0.013	0.013–0.020	0.020–0.030	1×d	0.1×d
N4	$v_c$					
N4	$f_z$					
N5	$v_c$	100–130	100–130	100–130		
N5	$f_z$	0.003–0.015	0.015–0.030	0.030–0.050	1×d	0.2×d
N6	$v_c$					
N6	$f_z$					
N7	$v_c$	120–150	120–150	120–150		
N7	$f_z$	0.003–0.015	0.015–0.030	0.030–0.050	1×d	0.2×d
N8	$v_c$	120–150	120–150	120–150		
N8	$f_z$	0.002–0.013	0.013–0.020	0.020–0.030	1×d	0.1×d
S1	$v_c$	30–50	30–50	30–50		
S1	$f_z$	0.002–0.012	0.012–0.018	0.018–0.025	1×d	0.2×d
S2	$v_c$					
S2	$f_z$					
H1	$v_c$					
H1	$f_z$					
H2	$v_c$					
H2	$f_z$					
H3	$v_c$					
H3	$f_z$					
O1	$v_c$	150–200	150–200	150–200		
O1	$f_z$	0.003–0.015	0.015–0.030	0.030–0.050	1×d	0.2×d
O2	$v_c$					
O2	$f_z$					
O3	$v_c$					
O3	$f_z$					

Genannte Werte sind Richtwerte, die je nach Maschine, Aufspannung, Kühlenschmierstoff usw. noch angepasst werden müssen.

Les valeurs mentionnées sont des valeurs recommandées qui doivent être adaptées selon les conditions de la machine, du serrage, du lubrifiant etc.

Questi valori sono valori raccomandati che devono essere adattati secondo le condizioni della macchina, del serraggio, del lubrificante etc.

These are recommended values that depend on the condition of the machine, fixture, coolant etc., and they may have to be adapted yet.